

1	書番号 ument No	ο.	ATAD-H1104-00						
Appr	oved	SJ.OK	(AMURA	20240422					
Che	cked	SZ.OI	NO	20240422					
Cha	rged	RI.GE	NDA	20240419					
Dra	awn	RI.GE	NDA	20240419					

Rev.	0
Dis No.	
Charged	
Checked	
Date	

当社の圧着端子に圧着使用される指定の電線は所定の圧着性能を得る為に、圧着品質基準書を満たすよう作業を実施し、クリンプハイトを次ページの通りに設定し管理願います。 Please control the crimp conditions shown next page for securing the specified performance. Please also do crimping based on the crimp quality standards.

■注意事項

- 1. クリンプハイト設定値を外れた場合は品質上の重大な事故となる可能性が有ります。クリンプハイトは品質を決める重要な要点の一つです。
- 2. クリンプハイトの調整方法及び測定方法は,取扱説明書を参照して下さい。 なお、被覆側のクリンプハイトは、電線メーカー、ロットの違い等により特定出来ない場合が有ります。
- 3. 弊社では、 芯線側クリンプハイトの最適値を精度よく設定する為に電線毎に試験を実施してクリンプハイトの設定をする事を原則としています。 上記以外の新たな電線のクリンプハイトの設定値につきましては、弊社営業本部までご連絡下さい。
- 4. 本圧着条件表は、弊社純正アプリケータを使用した場合に限り適用します。
- 5. 圧着条件は予告なく追加される場合があります。
- 6. UL File No.が同じ、かつ芯線構成・芯線めっきが同等の電線については、メーカー名によらず同等の圧着条件で圧着可能です。

■ Notice

- 1. Controlling the crimp height is an important task to decide the quality of the crimping. It may lead to a serious quality problem if the crimp height is not properly established.
- 2. Please refer to an instruction manual for the method of adjustment and measurement of the crimp height. The crimp height shown on the wire insulators will, in many case.

be for reference only as they will differ per each cable manufacturer and the production volume.

- 3. Hirose's internal rule is to establish a crimp height by performing a crimp testing on every wire in order to provide a precise crimp height strictly. As such, it is recommended that our sales representative are consulted, if any other wires are to be used besides these.
- 4. The crimp condition table is applied only if the tool specified by Hirose is used.
- 5. The crimp condition table is subject to be added without notice.
- 6. The wire which UL File No., its conductor construction and conductor plating are same can be crimped with same crimp condtion even if the wire manufacturer is different.

■特記事項 / Other items of note

圧着条件表 Crimp Condition Table

Ap	適用圧着端子 plicable Crimp Contact	圧着品質基準書
HRS No.	製品名 Product name	Applicable Crimp Quality Standards
544-0508-0-00	DF62-30SCFA	ATAD-H0642 ETAD-H0642

文書番号		ATAD-H1104-00							
Approved	SJ.Ok	AMURA	20240422						
Checked	SZ.OI	OV	20240422						
Charged	RI.GE	NDA	20240419						
Drawn	RI.GE	NDA	20240419						

Rev.	0
Dis No.	
Charged	
Checked	
Date	

	UL No./	AWG	メーカー名	芯線構成	芯線めっき	芯線材質 Conductor	被覆外径	被覆材質 Insulator	芯線部クリンプハイト Conductor Crimp Height		芯線部クリンプワイド Conductor Crimp Width		被覆部クリンプハイト Insulator Crimp Height		被覆部クリ Insulator C	リンプワイド Crimp Width	プワイド 圧着部強度MIN Minimum Crimp Barrel	適合アプリケータ	
110.	Recommended	Cable Name	size	Manufacture	Construction	Plating	Material	Insulator dia	Material	MIN	MAX	MIN	MAX	MIN	MAX	MIN	MAX	Tensile strength [N]	Applicable tool
AA	0	1061	30	日立金属 Hitachi 三山電線 Miyama	7/0.102	Sn	軟銅線 Copper-wire	0.82	PVC	0.50	0.56	-	-	1.40	1.50	-	-	8	AP105-DF62-30
AB																			
AC																			
AD																			
AE																			
AF																			
AG																			
АН																			
AI																			
AJ																			
AK																			
AL																			
AM																			
AN																			
АО																			
AP																			
AQ																			
AR																			