

圧着条件表

Crimp Condition Table

文書番号 Document No.		ATAD-T1051-00
Approved	AH.EDASHIGE	20240408
Checked	AH.EDASHIGE	20240408
Charged	TY.MOGI	20240406
Drawn	TY.MOGI	20240406

Rev.	0
Dis No.	
Charged	
Checked	
Date	

当社の圧着端子に圧着使用される指定の電線は所定の圧着性能を得る為に、圧着品質基準書を満たすよう作業を実施し、クリンプハイトを次ページの通りに設定し管理願います。
Please control the crimp conditions shown next page for securing the specified performance. Please also do crimping based on the crimp quality standards.

■ 注意事項

- クリンプハイト設定値を外れた場合は品質上の重大な事故となる可能性が有ります。クリンプハイトは品質を決める重要な要点の一つです。
- クリンプハイトの調整方法及び測定方法は、取扱説明書を参照して下さい。
なお、電線の被覆外径が電線メーカー、ロットの違い等により異なる場合、被覆部クリンプハイトは参考値となります。
- 弊社では、芯線側クリンプハイトの最適値を精度よく設定する為に電線毎に試験を実施してクリンプハイトの設定をする事を原則としています。
上記以外の新たな電線のクリンプハイトの設定値につきましては、弊社営業本部までご連絡下さい。
- 本圧着条件表は、弊社純正アプリケーションを使用した場合に限り適用します。アプリケーションは部品に割れ、欠け等の明らかな破損が無い状態で使用してください。
- 圧着条件は予告なく追加される場合があります。

■ Notice

- Controlling the crimp height is an important task to decide the quality of the crimping.
It may lead to a serious quality problem if the crimp height is not properly established.
- Please refer to an instruction manual for the method of adjustment and measurement of the crimp height.
The crimp height shown on the wire insulators will, in many case,
be for reference only as they will differ per each cable manufacturer and the production volume.
- Hirose's internal rule is to establish a crimp height by performing a crimp testing on every wire in order to provide a precise crimp height strictly.
As such, it is recommended that our sales representative are consulted, if any other wires are to be used besides these.
- The crimp condition table is applied only if the tool specified by Hirose is used.
Please use the applicator for parts in a state without the clear damage such as breaking or the miss.
- The crimp condition table is subject to be added without notice.

■ 特記事項 / Other items of note

圧着条件表
Crimp Condition Table

適用圧着端子 Applicable Crimp Contact		圧着品質基準書 Applicable Crimp Quality Standards
HRS No.	製品名 Product name	
756-2001-0 00	ZH05-2224PCF	
		ATAD-T0857-00 ETAD-T0857-00

文書番号		ATAD-T1051-00
Approved	AH.EDASHIGE	20240408
Checked	AH.EDASHIGE	20240408
Charged	TY.MOGI	20240406
Drawn	TY.MOGI	20240406

Rev.	0
Dis No.	
Charged	
Checked	
Date	

No.	UL No./ Cable Name	AWG size	メーカー名 Manufacture	芯線構成 Construction	芯線めっき Plating	芯線材質 Conductor Material	被覆外径 Insulator dia	被覆材質 Insulator Material	芯線部クリンプハイト Conductor Crimp Height		芯線部クリンプワイド Conductor Crimp Width		被覆部クリンプハイト Insulator Crimp Height		被覆部クリンプワイド Insulator Crimp Width		圧着部強度MIN Minimum Crimp Barrel Tensile strength [N]	適合アプリケーション Applicable tool
									MIN	MAX	MIN	MAX	MIN	MAX	MIN	MAX		
AA	FLRY-A	22	HWATEK	7/0.25	-	軟銅線 Copper-wire	1.30	PVC	0.75	0.81	-	1.36	1.55	1.65	-	1.47	60	AP105-ZH05-2224P
AB	FLRY-B	22	HWATEK	12/0.21	-	軟銅線 Copper-wire	1.40	PVC	0.75	0.81	-	1.36	1.55	1.65	-	1.47	60	AP105-ZH05-2224P
AC	FLR9Y	22	Gebauer & Griller	7/0.27	-	軟銅線 Copper-wire	1.30	PP	0.75	0.81	-	1.36	1.55	1.65	-	1.47	60	AP105-ZH05-2224P
AD	CIVUS	22	矢崎総業 Yazaki	7/円形圧縮 7/Compacted round strand	-	軟銅線 Copper-wire	1.10	PVC	0.75	0.81	-	1.36	1.35	1.45	-	1.47	50	AP105-ZH05-2224P
AE	FLR2X-A	24	Gebauer & Griller	7/0.21	-	軟銅線 Copper-wire	1.30	XLPE	0.67	0.73	-	1.36	1.40	1.50	-	1.47	33	AP105-ZH05-2224P
AF	PP ZH ID	22	ACOME	7/0.25	-	軟銅線 Copper-wire	1.25~1.35	PP	0.69	0.75	-	1.36	1.55	1.65	-	1.47	50	AP105-ZH05-2224P
AG																		
AH																		
AI																		
AJ																		
AK																		
AL																		
AM																		
AN																		
AO																		
AP																		
AQ																		
AR																		